

THE COMPANIES OF ROHRER'S INCORPORATED



Technical Data Sheet

187 Barn Dry

Gradation	
US Standard Mesh	% Passing
10	100.0
12	100.0
16	97.3
30	29.5
40	6.6
50	3.8
60	2.1
100	1.9
200	1.4

Chemical Analysis	
Calcium Carbonate (CaCO ₃)	85.21
Calcium Oxide (CaO)	47.72
Calcium Element (Ca)	34.08
Magnesium Carbonate (MgCO ₃)	10.03
Magnesium Oxide (MgO)	4.81
Magnesium Element (Mg)	2.88
Total Carbonates	95.24
Calcium Carbonate Equivalent	97.14

Properties	
Specific Gravity	2.65
Density Loose lbs/cu.ft	96.86
Density Rooded lbs./cu.ft	106.7

