



### Analysis Data Sheet

### C33 Natural Concrete Sand

Gradation	
US Standard Mesh	% Passing
#100	9.4
#50	30.7
#30	53.4
#16	69.6
#8	83.3
#4	95.4
3/8"	100.0
<b>FM</b>	2.58

