

THE COMPANIES OF ROHRER'S INCORPORATED



Technical Data Sheet

#185 Dry Lime

Gradation	
US Standard Mesh	% Passing
20	100.0
30	99.9
50	81.5
60	72.6
70	67.4
100	59.6
200	44.2

Chemical Analysis	
Calcium Carbonate (CaCO ₃)	83.87
Calcium Oxide (CaO)	46.97
Calcium Element (Ca)	33.55
Magnesium Carbonate (MgCO ₃)	11.35
Magnesium Oxide (MgO)	5.45
Magnesium Element (Mg)	3.26
Insolubles	4.78
Total Carbonates	95.22
Calcium Carbonate Equivalent	97.38
Effective Neutralizing Value (ENV)	78.62

